

RED ALERT

STRIPPABLE REINFORCED WATER-ACTIVATED TAPE

DESCRIPTION

Pre-printed, "tamper-resistant" Red Alert is an oversized, reinforced, strippable natural kraft colored carton sealing tape manufactured with water-activated adhesive. It features a red colored bottom sheet which leaves behind a tell-tale red layer when removal is attempted. The oversized width prevents these residual red fibers from being concealed by re-taping with a single strip of 3" (76 mm) wide tape.

PRODUCT APPLICATION

Provides protection and security against tampering and/or pilferage of carton's contents. Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads. Recommend usage on average carton up to 40 pounds (18 Kg)

PHYSICAL PROPERTIES:

Caliper	6.3 mils (0.16 mils)
MD Tensile	74 lb/in (324 N/25mm)
CD Tensile	26 lb/in (114 N/25mm)

ADHESION (WATER AT RECOMMENDED 110°F/43°C):

Fipago:	
2/0	49
2/1	71
5/0	75
15/0	90
McLaurin:	86



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
Customer Service: 800.IPG.8273 | 800.474.8273
Tape Technical Service: 877.447.4832
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard terms and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 03/16

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

CONSTRUCTION PER 3,000 SQUARE FEET (metric)

Top Ply:	23 lb (37 g/m ²) Natural Kraft Paper (virgin fibers)
Bottom Ply:	23 lb (37 g/m ²) Natural Kraft Paper (virgin fibers)
Laminating Adhesive:	High Melt Index Polypropylene Based Co-Polymer
Water-Activated Adhesive:	Chemically Grafted Starch Based Copolymer Adhesive, Designated as S3911
MD Reinforcement:	(1-1-1-1-1) 75 Fiberglass (per 3"), 1/2" spacing
CD Reinforcement:	(1-1-1) 150 Fiberglass, 1.10" spacing, 43 degree angle

